



RMC RYMCO®

Rigid Metallic Conduit

RYMCO®
C A L I D A D 3 6 0



- Standards Compliance : ANSI C80-1 Underwriters Laboratories UL 6.
- Hot dipped galvanized on both exterior and interior surfaces with the best quality molten Zinc.
- Threads are galvanized after cutting.
- Used for industrial installations in electrical systems.
- Standard length: 10 feet.
- Coupling included.
- Protection : provides exceptional physical protection, reduces exposure to EMF, shields against Electro-Magnetic Interference (EMI) and provides an excellent electrical path to ground.



Tubería Conduit Rigida / Rigid Metal Conduit Steel RMC

Diametro Nominal Nomial Size		Peso 10 Tramos 10 Unit Lengths		Diametro Externo (1) Outside Diameter (1)		Espesor Nominal (1) Nominal Thickness (1)		Color de Cinta Tape Color	Piezas x Atado Pieces x Bundle	Piezas x Paquete Pieces x Lift
in.	mm.	lb.	kg.	in.	mm.	in.	mm.			
1/2"	16	82	37.20	0.840	21.34	0.104	2.64	Black	10	250
3/4"	21	109	49.44	1.050	26.67	0.107	2.72	Red	5	200
1"	27	161	73.03	1.315	33.40	0.126	3.20	Blue	5	125
1 1/4"	35	218	98.88	1.660	42.16	0.133	3.38	Red	---	90
1 1/2"	41	263	119.30	1.900	48.26	0.138	3.51	Black	---	80
2"	53	350	158.76	2.375	60.33	0.146	3.71	Blue	---	60
2 1/2"	63	559	253.56	2.875	73.03	0.193	4.90	Black	---	37
3"	78	727	329.77	3.500	88.90	0.205	5.21	Blue	---	30
3 1/2"	91	880	399.17	4.000	101.60	0.215	5.46	Black	---	25
4"	103	1030	467.21	4.500	114.30	0.225	5.72	Blue	---	20
5"	127	1400	635.00	5.563	141.30	0.255	6.50	Blue	---	15
6"	155	1840	834.62	6.625	168.28	0.266	6.76	Blue	---	10

Nota : Tolerancias Aplicables Largo / Length : 10 Ft. (3.05m) Coupling + / - 1/4 in. (+ / - 6mm)

Note : Applicable Tolerances (1) Solo informativo no requiere UL For Info. Only not a UL requirement.

Conduit RYMCO, makes no warranties expressed or implied including warranty of merchantability or fitness for a particular purpose. The specifications, descriptions, information and illustrated materials here in are submitted solely for evaluation by others and since the use of its information is not within its control, Conduit RYMCO assumes no obligation or liability for such information and does not guarantee result from the use of said products or the information herein. Reference should be made to the original or primary source data along with standard accepted industry practice. The material included here is from the date of publication and is subject to the possibility of change without prior notice. For certification see contact information.